

## TECHNICAL DATA:

We manufacture and supply wide range of high quality graded Acid Proof Cements, Resins and its allied products as below

<b>Properties</b>	<b>Furane</b>	<b>Phenolic</b>	<b>K-Silicate</b>	<b>Cnsl</b>	<b>Sulphur</b>	<b>Epoxy</b>	<b>Polyester</b>	<b>Bricks</b>
Colour	Black	Black	Off White	Black	Black	Off White	Off White	Red/White
Ratio ( Solution Powder)	1:3	1:3	1:3	1:3	Hot melt	1:5	1:5	-
Compressive Strength ( kg/cm <sup>2</sup> )	350	350	150	280	250	500	500	700
Flexural Strength (kg/cm <sup>2</sup> )	75	75	40	75	70	150	150	200
Bond Strength (kg/cm <sup>2</sup> )	10	10	05	10	10	10	12	-
Water Absorption (max %)	01	01	18 *	01	01	01	01	02
Temperature Resistant (max c)	170	170	900	190	90	90	90	900
Self Life @ 27 °C	60 days	45 days	365 days	90 days	Life Time	90 days	90 days	Life time